

Caponago 29/04/2020

## RI-121/100 Slip Resistance approval

04741 RI-121/100 CLEAR AP940 PERMANENT WG62 overlamine film has been tested in accordance with the guidelines recommended by the UK Slip Resistance Group:  
<http://www.ukslipresistance.org.uk/index.php?id=guidelines>. "The Assessment of Floor Slip Resistance" - Issue 3 2005

The UK Slip Resistance Group comprises members from flooring and associated industries and includes flooring manufacturers, representatives of the Health and Safety Executive, test houses, end users, instrument manufacturers, and forensic engineers.

*Standard Reference* DIN 51130:2010 Testing of Floorcoverings – Determination of Slip resistance work rooms and areas of work with an increased risk of slipping - Walking method - Ramp test.

Test	Inclined Platform Shod
Mean Value	7.5°
Rating	R9

### *R rating category:*

R value	Category Static Friction is:	Angle of Inclination
R9	Low	6° to 10°
R10	Normal	10,1° to 19°
R11	Above Average	19.1° to 27°
R12	High	27.1° to 35°
R13	Very High	> 35°

### *Note to end use applications:*

R9 Floors in work rooms and work areas without a high risk of slipping. General and private areas.  
R10 to R13 Floors in workrooms and work areas where there is an increased risk of slipping due to grease, oil, water, foods, left-overs, dust, flour, plant clippings, etc..